



VersaFlex Incorporated  
 87 Shawnee Avenue  
 Kansas City, KS 66105  
 (913) 321-1416  
 (913) 321-1490 (fax)

## Material Processing & Handling Information

**Material:** TopSeal

**Material Type:** Penetrating Surface Sealer

**Application:** Concrete or Masonry Surfaces

**Application Process:** Spray, Roll or Brush

<b>Process Equipment:</b>	<b>Pumps</b>	<b>Dispensing Gun</b>
<b>Graco:</b>	390 Airless Sprayer (or similar)	FTX (or similar)
<b>Generic:</b>	Diaphragm or 1:1 Piston Pump	Use agricultural spray gun & tips
<b>Generic:</b>	Pump-Up Sprayer	Included
<b>Process Temperature:</b> Ambient (use above 32°F)		
<b>Process Pressure:</b> 10 to 500 psi		
<b>Moisture Content:</b> Moisten slab prior to application. Saturate surface but do not allow standing water.		
<b>Application Temperature:</b> 32°F and higher.		
<b>Dew Point:</b> N/A		
<b>Surface Prep (as sealer only):</b> High pressure water blast, sand, grind or abrasive blast to remove any contaminants that may interfere with penetration of TopSeal.		
<b>Application:</b> Apply in one or two coats using spray, roller or brush. Avoid ponding of material on horizontal surfaces.		
<b>Application Rates:</b> Concrete: 100 to 200 square feet per gallon depending on substrate porosity and surface profile.		
<b>Storage Temp</b>	<b>Storage</b>	<b>Special Handling</b>
Above Freezing (32°F)	Keep dry. Keep from freezing. Store in covered temperature controlled environment if possible.	Keep containers closed and protected from atmospheric contamination.
<b>Safety:</b> Please consult product MSDS for full details.  Safety glasses, Rubber gloves, Protective clothing, Organic vapor or fresh air respirator.		